



CIAQUISTAB PBP-533

Stabilizer - lubricant

DATASHEET

Update

July 04, 2014

Page 1 of 1

CHARACTERISTIC	INSPECTION	VALUE	METHOD
Appearance	Visual	White or light yellowness powder	137 LAB T
Contamination	Comparative	Standard	142 LAB T
Content of Pb	% PbO	56.1 – 57.7	145 LAB T
Heat stability	Ratio	Min 0.96	152 LAB T

The given information is based on data that we consider correct and provided in good faith. In spite of it and when being the methods and use conditions outside of our control, we suggest the user to determine the performance of our products before adopting them to industrial scale.

Packing
<ul style="list-style-type: none"> Polypropylene bag laminate with polyethylene Net weight: 25 kg
Export packing
<ul style="list-style-type: none"> The bags are packing on wood pallets. The pallets are fixed with plastic band. The pallets are covered with polyethylene shrink on film. <p>Size: Base: 110 cm x 110 cm Height: changeable</p> <p>Net weight max.: 1000 kg</p> <p>Gross weight max.: 1035 kg</p>

Usos principales
<p>CIAQUISTAB PBP-533 is a system indicated for PVC fittings injection. Its main features are a high thermal stability and a perfect balance of internal and external lubrication.</p> <p>It's a system that with an added only one introduces all the auxiliary necessary to do a correct processed of rigid PVC and to obtain the properties needed in the final product. It reduces the operation cost.</p> <p>The use proportions is between 4.0 to 6.0 phr, you can also use acrylic process aid between 1 and 2 phr.</p>



This product is manufactured under the controls settled down by our System of Management of Quality and Management of Environment that it fulfills the requirements of the norms ISO 9001 and ISO 14001, which has been certified by Bureau Veritas



COMPAÑÍA QUÍMICA S.A.

Phone (51-1) 514 8700 e-mail: ventas@ciaqui.com.pe